



## Thermal Transfer Ribbon Technical Data Sheet

# TRX-50 General Purpose Wax/Resin

### Product Description

TRX-50 features a SmoothCoat® backcoat and is the only wax/resin ribbon on the market backed by a versatile and durable wax/resin ribbon that has superior print quality on low-end synthetics. TRX-50 prints at low temperatures and high speeds and has unbeatable edge definition with the darkest images possible from a general purpose ribbon.

### Recommended Applications



ASSET TRACKING



AUTOMOTIVE



FLEXIBLE PACKAGING



GENERAL



HEALTHCARE



HORTICULTURE



INVENTORY



LOGISTICS



MEDICAL DEVICES



OUTDOOR



PARTS PACKAGING



PHARMACEUTICAL



PRODUCT ID



RETAIL



RFID



SHELF



SHIPPING



SIGNAGE

### Recommended Substrates

Gloss paper, polpropylene, top-coated vinyl, polyethylene, polystyrene, coated/uncoated Valeron®, polyolefin, coated/uncoated V-max®, Tyvek®, Tyvek Brillion®

### Performance Characteristics

- Halogen-Free
- Backed by our 4 Million Linear Inch Guarantee
- Prints at high speeds (12 IPS) delivering crisp, rotated bar codes
- Features a SmoothCoat® backcoat
- Anti-static for easy handling and extended printhead life
- Superior print quality on low-end synthetics
- Industry leading edge definition for clean, durable, and dense bar codes



## Thermal Transfer Ribbon Technical Data Sheet

# TRX-50 General Purpose Wax/Resin

### Ribbon Properties

Description	Result	Test Method
Ink	Wax/Resin	
Color	Black	Visual
Total Thickness	8.1 ± 0.5μ	Micrometer
Base Film Thickness	4.8 ± 0.3μ	Micrometer
Ink Thickness	3.3 ± 0.2μ	Micrometer
Ink Melting Point	85°C (185°F)	Differential Scanning Calorimeter

### Durability of Printed Image

Label Stock: Polypropylene

Print Speed: 6 IPS

Description	Result	Test Method
Print Density	> 1.80	Densitometer
Smudge Resistance	A*	Colorfastness Tester - 50 Cycles @ 500 Grams with Cotton Cloth
Scratch Resistance	A*	Colorfastness Tester - 20 Cycles @ 200 Grams with Stainless Steel Pointed Tip

\*American National Standard Institute (ANSI) Grade Levels A, B, C, D, and F, where A is excellent, B is above average, C is average, D is below average, and F is poor.

### Conversion Chart

Millimeters (mm) to Inches = mm ÷ 25.4	Inches to Millimeters (mm) = Inches ÷ 0.03937
Meters (m) to Feet (ft) = m ÷ 0.3048	Feet (ft) to Meters (m) = Feet ÷ 3.2808
C° to F° = (1.8 X C°) + 32 = F°	F° to C° = (F° ÷ 1.8) - 17.77
Thousand square inches (MSI) to m <sup>2</sup> = MSI X 0.645	MSI = m <sup>2</sup> ÷ 0.645

*The information on this data sheet was obtained in our laboratories. Measured values may vary slightly when tested in a different environment. Information contained within this document is subject to change without notification.*